



Epoxy &
Polyurethane
Manufacturing and
Research

TECHNICAL BULLETIN

Coefficient of Friction Table

Product	Neoprene*	Leather*
SS 1120	1.16	0.93
SS 1202	0.806	0.675
SS 1540	0.856	0.825
SS 1600	0.95	0.625
SS 2700	0.95	0.744
SS 3300	0.719	0.544
SS 3500	0.806	0.675
SS 3700	0.819	0.631
SS 3700 CF	0.863	0.778
SS 3800	0.900	0.705
Rembrandt Polymer Stain	0.966	0.916
Stone Tone Sealer II - Gloss	0.958	0.883
Stone Tone Sealer II - Satin	0.862	0.800
Easy Shine - Gloss	0.913	0.651
Easy Shine - Satin	0.887	0.775

*Test Method MIL-PRF 24613 (Paragraph 4.8.6) – Typical Results

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.

Service is part of our formula

Epmar Corporation
13210 Barton Circle, Santa Fe Springs, CA 90605-3254
Ph: 562.946.8781 / Fax: 562.944.9958
E-Mail: epmar@quakerchem.com Web Site: www.epmar.com